

**1.**

CREAMIDE 66 R200

66

가

1415-3

TEL : 054 931 1488

2006 1 3

2011 10 1

**2.**

	<u>CAS No.</u>	<u>(%)</u>
Polyamide 66	32131-17-2	
가	-	< 1

**3.**

NFPA	(0-4 )	=1,	= 1,	= 0
1)	,	,	가	가
2)	,	,	, 가	
3)	.	.	.	
4)	.	.	.	
5)	.	.	.	
6)	.	.	.	

---

**4.**

---

1)

2)

3)

4)

5)

---

**5.**

---

1) ( )

2)

3) /

4)

5)

가

6)

7)

가

---

**6.**

---

1)

가

2)

3)

**7.**

- 1)
- 2)

**8.**

- 1)
- 2)
- 
- 
- 
- 
- 3)
- 
- 
- 

(A.C.G.I.H)

가  
가

**9.**

- 1)
- 2)
- 3) pH
- 4)
- 5) /
- 6) /
- 7)
- 8)
- 9)
- 10)
- 11)
- 12)
- 13)
- 14)

(R.V.)

255 ~ 265 °C

1.12 ~ 1.15

---

**10.**

---

1)

2)

\*

\*

3)

4)

---

**11.**

---

1)

2) /

3)

4) ( )

5)

---

**12.**

---

1)

2)

3)

4) 가

---

**13.**

---

1)

2)

---

**14.**

---

- 1)
- 2)
- 3)

---

**15.**

---

- 1)
- 2)

---

**16.**

---

- 1)                    :                    (MSDS)                    41                    96-12
  
- 2)
  
- 3)                    CAS                    가
  
- 4)                    :